



## SHADE FABRIC SPECIFICATIONS

JULY 2012  
1111X 3033

### IDEAL FOR:

**SHADE SAILS, SHADE STRUCTURES, PERGOLAS, TRUCK TARP, FENCING & SCAFFOLDING**

<b>ROLL WIDTH:</b>	325cm
<b>ROLL LENGTH:</b>	50 metres
<b>NOMINAL WEIGHT:</b>	370gsm
<b>FABRIC TYPE:</b>	HDPE Monofilament yarn
<b>TREATMENT:</b>	UV & FR
<b>COLOURS:</b>	Summit Cream, Southern Sand, Thibault Blue, Spartan Green & Precision Grey
<b>WARRANTY:</b>	10 year UV warranty under tension



Summit Cream



Southern Sand



Thibault Blue



Spartan Green



Precision Grey

### Engineering Specifications

Breaking Force - Warp (AS2002.3.1-2001)	1433N/50mm
Breaking Force - Weft (AS2002.3.1-2001)	2210N/50mm
Elongation at Break - Warp	97.9%
Elongation at Break - Weft	73.5%
Tear Resistance/Wing Rip - Warp AS2001.2.10.1986	215N
Tear Resistance/Wing Rip - Weft AS2001.2.10.1986	323N
Bursting pressure (AS2001.2.4-16990 Mean Hydraulic Diaphragm)	4750kPa
Bursting Force (AS 2001.2.19-1988 Mean Steel Ball)	3011N



Tested to AS1530.2 & AS1530.3. Results available on request.

Please refer to your Monotec FR sample book for colour options.

For pricing information, please refer to your Ricky Richards Price List for Structure & Membrane Fabrics or contact the Ricky Richards (Sales) team on 02 9735 3333.